Minor Amendment of the Local Free Energy

On Excluded Volume Problem

Kazumi Suematsu

Institute of Mathematical Science
Ohkadai 2-31-9, Yokkaichi, Mie 512-1216, JAPAN
E-Mail: suematsu@m3.cty-net.ne.jp, Tel/Fax: +81 (0) 593 26 8052

arXiv:1012.2505v1 [cond-mat.soft] 12 Dec 2010

1 Local Free Energy

Amendment is necessary for the classic theory of the local free energy [1] to be applied in a more rigorous manner to real polymer solutions. As is well known, the classic theory for the local free energy does not take into consideration correctly the interaction between segments on the same chain, so that the classic theory is constructed on the basis of the *pseudo* self-avoiding chains whose behavior is virtually identical to that of the ideal chain. This feature has been frequently criticized so far by physicists as a fundamental deficiency of the Flory theory.

Let us consider the three dimensional lattice where a site may be occupied by a segment or a solvent molecule. Let a site be surrounded by z neighboring sites, and let there be δx segments from different molecules in the volume element δV. The number of arrangements of those segments is

$$\Omega_{\delta V} = \prod_{i=0}^{\delta x-1} (z_i - 1)(1 - f_i) \tag{1}$$

where f_i is the probability that a given cell is occupied by the polymer segments when i segments are already put in δV, so that $f_i = i/\delta n_0$ where $\delta n_0 = \delta x + \delta n_1$, δn_0 denotes the total number of sites and δn_1 the number of solvent molecules in δV. z_i is a special number introduced in this amendment and is defined by $0 \leq z_i \leq z$. The physical meaning of z_i is as follows:

> There is finite probability that a given segment overlaps with the other segments on the same chain (the multioccupation problem). Such unphysical conformations must properly be removed by subtracting from the total number $\prod_i (z-1)$ of feasible conformations. This is possible, because the number of conformations is enumerable in principle. The subtraction can be achieved simply by reducing z to z_i, so that $\prod_i (z_i - 1)$ represents the total number of self-avoiding conformations. To date the numerical value of z_i is unfortunately unknown, which however is not essential for the present purpose, as is verified below.

By eq. (1) the local entropy becomes

$$\delta S = \delta S_{mixing} + \delta S_{melting} = k \log \Omega_{\delta V} = k \left\{ \sum_{i=0}^{\delta x-1} \log (z_i - 1) + \log \frac{\delta n_0!}{\delta n_0^{\delta x} (\delta n_0 - \delta x)!} \right\} \tag{2}$$

Applying the Stirling formula to the above equation, we have

$$\delta S_{mixing} + \delta S_{melting} \cong -k \left\{ \delta n_1 \log v_1 + \delta x - \sum_{i=0}^{\delta x-1} \log (z_i - 1) \right\} \tag{3}$$

where $v_1 = (\delta n_0 - \delta x)/\delta n_0$ is the volume fraction of solvents. The melting entropy, $\delta S_{melting}$, can be obtained by putting $\delta n_1 = 0$ in eq. (3). Hence we have

$$\delta S_{mixing} = -k \, \delta n_1 \log v_1 \tag{4}$$

which is exactly the Flory result. It turns out that all the self-avoiding terms are absorbed into the melting entropy, $\delta S_{melting}$. Noteworthy is the fact that the mixing entropy δS_{mixing} of the *pseudo* self-avoiding chains and solvent is exactly equal to that of the genuine self-avoiding chains and solvent; only the standard state must be altered as

$$\text{pure } \textit{pseudo} \text{ self-avoiding chains} \quad \Rightarrow \quad \text{pure } \textit{genuine} \text{ self-avoiding chains.}$$

This unexpected result does not appear to have been fully recognized by theorists up to present. A close investigation however tells us that the result is by no means surprising, because by eq. (4) δS_{mixing} is a function of the solvent fraction alone, but unrelated to the conformational properties of chains.

Adding the enthalpy term, $\delta H_{mixing} = kT\chi\delta n_1 v_2$ to the above equation, we have the formula of the local free energy in the volume element δV

$$\delta F_{mixing} = \delta H_{mixing} - T\delta S_{mixing} = kT\left\{\log\left(1 - v_2\right) + \chi v_2\right\}\delta n_1 \tag{5}$$

where $v_2 = 1 - v_1$ is the volume fraction of the segments. Eq. (5) represents the free energy difference between the mixture of the self-avoiding chains and solvent, and the respective pure components. Eq. (5) has already been derived by Flory [1].

We realize that eq. (5) has deeper generality along with sound physical basis, and hence is applicable equally to the excluded volume problem over all concentration range.

References

[1] P. J. Flory. Principles of Polymer Chemistry. Cornell University Press, Ithaca and London (1953).